

Single cell coordination

Single cell list

Number	Current location	Main purpose	Current status	Notes
TE1AES004	FNAL/A0	Equator pit quenching, T-map	To be HPR to clean away FE.	
TE1AES005	FNAL ICB	CMP, EP, ABLE	To be HF rinsed	
TE1ACC001	ANL	FE	HPR to clean away FE	
TE1ACC002	CABOT	CMP	RF test done, to be polished at CABOT	
TE1ACC003	FNAL/IB1	laser remelting	To be tested.	
TE1ACC004	JLAB	Tumbling	Baking in progress, to be shipped back this week	
TE1ACC005	ANL	Eddy current scanning	EP completed, to be HPR and test	
TE1ACC006	FNAL_ICB	Eddy current scanning	To be progressive EP	
NR-1	ANL/APS	APS Furnace qualification	to be baked	
NR-4	ANL	ABLE EP	To be HPR/Baking	
NR-5	FNAL/ICB	E-beam remelting on Pit	inspected, to be processed	
NR-6	FNAL/ICB	Laser re-melting	equator weld pit	
TE1PAV001	PAVAC			
TE1PAV002	PAVAC			
TE1PAV003	PAVAC			
TE1PAV004	PAVAC			
TE1PAV005	PAVAC			
TE1PAV006	PAVAC			
TE1PAV007	PAVAC			
TE1RRC001	to be made at RRCAT			
TW1AES001	MDTL	Traveling wave prototype	Cavity inspection, Tooling design for BCP	
TW1AES002	MDTL	Traveling wave prototype	Cavity Inspection	

Legend:

Last week activity

This week activity

Summary

- TE1ACC004, baking on Monday
- NR-1, baking this week
- TE1ACC003, test on Tuesday
- TE1ACC005, EP 150 minutes, to be tested
- TW1AES001&002, inspection completed