



Module PXFEL2_1

Initially assembled and tested at DESY

Disassembly at DESY ongoing


Parts to be shipped to Saclay for re-assembly

History: Test 1

- **26.1 MV/m with strong FE**

Test 2

- **After additional HPR**
- **40.2 MV/m**



As reported in previous meeting:

- Test 4 (additional 120 um EP)
- **45.8 MV/m, Q=1.3E10, no FE**

Ongoing:

- Test 5
- **Additional HPR (needed due to accidental venting)**
 - **With Tmap**